

HYDROTEK

FLUORESCENT PRINTING INK SERIES

HydroTek water-based inks are formulated for narrow-web flexo printing onto various substrates for the production of self-adhesive labels.
In addition to the standard ink series, a range of daylight fluorescent inks is also available.

KEY FEATURES

- Formulated to give a strong and bright fluorescent effect
- Good printability and press-stability characteristics
- Supplied press-ready at optimum printing viscosity
- High coverage and transfer on absorbent substrates
- Good scratch and rub resistance
- Suitable for all paper stocks

PRODUCT REFERENCES

REFERENCE	DESCRIPTION
40W5 0802	HYDROTEK FLUORESCENT 802 GREEN
40W5 0803	HYDROTEK FLUORESCENT 803 YELLOW
40W5 0804	HYDROTEK FLUORESCENT 804 ORANGE
40W5 0805	HYDROTEK FLUORESCENT 805 RED
40W5 0806	HYDROTEK FLUORESCENT 806 PINK
40W5 0809	HYDROTEK FLUORESCENT 809 YELLOW

Other colours can be mixed upon request

PRINTING GUIDELINES

General

- Shake the container well before use. Clean printing press thoroughly prior to printing.
- Ensure underlying inks are dry before overprinting.
- Synthetic substrates should be pre-treated and tested to ensure adequate ink adhesion.
- Rub and other resistance properties should be checked dependent upon application.
- Short production runs should be used to confirm that the desired results are achievable.
- High ink film weights may enhance the colour effect but ensure that the ink is thoroughly dried.

Printing Plates

HydroTek inks are suitable for printing with most plate materials recommended for water-based inks. Consult with your plate supplier if in doubt.

Zeller+Gmelin UK Ltd.
Queensbridge Industrial Park,
795 London Road,
West Thurrock, Essex,
RM20 3LH

Tel: +44 (0)1708 89 90 91
info@zeller-gmelin.co.uk
www.zeller-gmelin.co.uk

Anilox Rollers

Colour strength is highly dependant upon anilox roll configuration. A minimum cell volume of 8 cm³/m² is recommended to ensure sufficient ink coverage.

Substrates

Papers – HydroTek inks are designed to be used on both uncoated and coated papers. Scuff, smudge, water and moisture resistance may vary dependant upon the ink filmweight, type of paper and drying conditions. Full adhesion, water and moisture resistance may take up to 24 hours to develop

Thermal Papers – We recommend that thorough testing is made to ensure suitability prior to commencing a full print run. Resistance properties may be enhanced by over-lacquering with one of our water-based or UV-curing varnishes. Please consult us for a product recommendation.

Plastics - Surface energy levels of between 38 – 42 dynes/cm are recommended; this may be achieved by pre-treatment using corona discharge, flame, plasma or other methods. Inline pre-treatment usually gives the best results. Production testing is always recommended to ensure adequate ink adhesion and resistance properties. Very high surface treatment levels may result in poor water resistance. Please consult us for recommendations for difficult substrates.

Hot-foil Stamping

HydroTek inks are generally suitable for hot-foil stamping. Results may vary dependant upon the ribbon and processing conditions.

Laser Overprinting

HydroTek inks are not suitable for laser overprinting.

Printing Speeds

The following print speeds are typical:

	Process Colours	Line Colours / Solids
Print Speed (m/min)	100 -150	80 - 150

Dryer temperatures should be at least 50°C with maximum airflow to ensure sufficient drying. Higher print speeds might be achievable on presses with combination IR and hot air dryers.

Resistance Properties

Optimum resistance properties normally do not develop for at least 24 hours. For enhanced chemical and other resistance properties we recommend over-lacquering with one of our water-based or UV-curing varnishes. Please consult us for a product recommendation.

Cleaning

Wet and partially dry HydroTek inks can be cleaned with *40W9 0004 Wash-Up Solution*.

40W9 0017 Superclean Wash is recommended to remove dry ink as well as deep cleaning of anilox rollers.

Zeller+Gmelin UK Ltd.
Queensbridge Industrial Park,
795 London Road,
West Thurrock, Essex,
RM20 3LH

Tel: +44 (0)1708 89 90 91
info@zeller-gmelin.co.uk
www.zeller-gmelin.co.uk

Additives

A full range of press-side additives is available to cover any requirements:
See separate data sheet for complete application and ink troubleshooting guidelines.

Reference	Description	Comments
40W9 005	Accelerator	Use up to 5% to increase drying speed
40W9 006	Retarder	Use up to 5% to slow down drying speed
40W9 007	Antifoam	Add 2 - 4% to control any foaming issues
40W9 009	Stabilising Varnish	Use to maintain ink pH and viscosity
40W9 0012	pH Refresher	Use on long print runs to maintain pH
40W9 0013	Reducer	Use to reduce ink viscosity
40W9 0014	Transfer Additive	Use up to 5% to increase transfer and colour
40W9 0015	Wax Additive	Use up to 5% to improve scratch and scuff
40W9 0016	Silicone Additive	Use up to 5% to increase slip properties
40W9 09295	Slow Retarder	Use up to 3% to slow drying speed significantly
40W9 0004	Wash-Up Solution	For general purpose cleaning
40W9 0017	Superclean Wash	For heavy duty cleaning

Storage

Store at ambient temperatures in sealed containers. Protect from frost.
Nominal shelf life is 6 months in correctly stored, unopened containers.

Packaging

Standard packaging is 5.0 kg plastic containers.

Health & Safety

Please refer to the product Safety Data Sheets.
Good industrial hygiene should always be practiced with these types of products. Use personal protection equipment as specified by the SDS.

Waste Disposal

Please refer to the SDS.

Organoleptic Properties (Taint and Odour)

If tested, the products may be suitable for certain low odour applications.

Migration

Paper, carton and plastic materials such as PE or PP normally do not offer a sufficient barrier to prevent migration of low molecular weight ink or varnish components. Glass, metal and some metallised laminates are usually more efficient as functional barriers. There should be no visible set-off of ink onto the food contact side of printed material. Packaging and processing should be designed such that there is no possibility for continuous ink contact with foodstuffs.

Zeller+Gmelin UK Ltd.
Queensbridge Industrial Park,
795 London Road,
West Thurrock, Essex,
RM20 3LH

Tel: +44 (0)1708 89 90 91
info@zeller-gmelin.co.uk
www.zeller-gmelin.co.uk

Food Compliance Declaration

Please refer to separate documentation. HydroTek inks are not suitable for direct food contact.

Within the European Union (EU) it is the responsibility of the manufacturer, importer or distributor of food contact materials and articles, or those who place them in contact with food prior to sale, to ensure that their products comply with the appropriate legislation.

We therefore strongly recommend that the final printed article is analysed by an accredited institute to ensure legal compliance before putting it into circulation.

Declaration of Composition

Please refer to separate documentation.

Please contact us for any questions regarding the suitability of this product for a particular application or compliance to a particular standard.